

# FENCE PRO BLACK

## ACRYLIC LATEX WATER-BASED FENCE & BARN PAINT

Direct from the  
Heart of Horse  
Country!

### DESCRIPTION

100% acrylic latex water-based paint formulated especially for wood plank fences and barns.

### FEATURES

- Self-priming.
- Non-toxic – soap and water cleanup.
- Flexibility resists chipping and peeling.
- Offers exceptional economy and durability in a user-friendly water-based formulation.
- Provides excellent weather protection and decoration.
- Safe around valuable horses and livestock.
- Can be applied directly to new, weathered or previously painted lumber.
- 3 to 6 years of durability on plank fence, depending on fence condition and surface preparation. Initial coat on new wood will age quicker than recoats.

### RECOMMENDED USES

- Plank fences
- Barns
- Farm buildings
- New and weathered wood
- Concrete, masonry, and brick
- Metal structures and properly primed steel – product will not prevent rust
- Not suitable for flooring or high abrasion surfaces

### CHARACTERISTICS

Color	Black
Finish	Semi-gloss
Flash point	> 201°F (PMCC)
Viscosity	88 KU
Available Packaging	5-gal pails, 55-gal drums, 250-gal totes
VOC	Less than 250 grams/liter
To increase flexibility and durability, product will dry softer than conventional paints and may retain a slight tack.	

### SHELF LIFE

2 years unopened, stored out of direct sunlight at temperatures between 40°F and 90°F.

Settling can occur, product must be shaken vigorously before use. For best results, flip pails upside down while shaking.

**Do not freeze.**

### COVERAGE

3 & 4 board fence	16 ft. / gal., both sides
1 board fence	26 ft. / gal., both sides
Barns	250 sq. ft. / gal.

Typical fence posts are placed 8 feet apart.

Coverage depends on many factors such as porosity and roughness of the substrate and material losses during application. Using less material than recommended will see a decrease in durability. May require two coats for best results – especially on new wood.

### DRYING TIME @ 77°F / RH 50%

Set to touch	1 hour
Re-coat	4 hours
Fully dry	24 hours

Drying times are affected by rain, dew, and temperature. Do not paint if rain is expected within 8 hours.

### RECOMMENDED FILM THICKNESS

Wet film – per coat	6.0 to 10.0 mils
Dry film – per coat	2.0 to 4.0 mils

### APPLICATION

Product should be thoroughly mixed before use. No thinning needed – if necessary, thin with 4 fl. oz. water per gal. paint.

Application temp.	above 50°F
Method	Brush, roll, or spray

Allow new wood 1 to 3 months to weather to reduce moisture content (less than 15% is recommended.)

**Do not paint the underside of fence planks.**

Airless spray:

Rating	0.5 gallons / minute minimum
Pressure	1800-2500psi
Filter	30 to 60 mesh
Tip Size	0.017" to 0.025"

Roller application: use thick nap 7" roller.

### SURFACE PREPARATION

For greatest durability make sure surface is scraped or pressure washed thoroughly to remove any peeling or flaking paint before applying.